

ZL Brown 130

02-703 | Technical Data Sheet



Technical Information

Plies	1
Overall Thickness	.25"
Tensile Force	150# @ 1%
in N/mm	26
Standard Tension	.5%
Min. Pulley	3"
Min. Back Flex	6"
Weight	1.09 Lbs/SF
Product Operational Temp. Range	0° to 250° F
Hardness	60 Duro Shore A
Max. Width	72"

Material Construction

Conveying Surface

Compound	Nitrile
Cover Surface	Rough Top
Color	Brown

Underside

Fabric	Ziplink Polyester
Bottom Surface	Friction
Coefficient of Friction	.4

Standard Fabrications

Longitudinal Splice	No
Guide Applied to Cover	No
Sidewalls	No
Edge Capped	No
Cleats	No
Guide Applied to Bottom	Yes
Mechanical Lacing	No

Features

FDA	No
Anti-Microbial	No
Anti-Static	No
Flame Retardant	No
Cross Rigid	Yes
Troughing	No
Curve Belt Compatible	No

ZL Brown 130

02-703 | Splicing Instructions

High Speed Press Settings

Pressure No Settings
 Temp. Top
 Temp. Bottom
 Dwell Time
 Foil Position
 Foil
 Release Top
 Release Bottom

Water Cooled Press Settings

Pressure No Settings
 Temp. Top
 Temp. Bottom
 Dwell Time
 Foil Position
 Foil
 Release Top
 Release Bottom

Compatible Splices

Endless Splices

Step Splice	No
Straight Finger	No
Split Finger	No
Bias Finger	No
Skive	No
Finger Over Step	No
Step Over Finger	No
Electrode	No
Butt Weld	No
Lock Lap	No

Mechanical Splices

Clipper	No
Alligator	No
Staple	No
Minet	No
Plastic Spiral	No
Plastic Rivet	No
Plastic Hinge	No
Super Screw	No
Bolt Hinge	No
Rivet Hinge	No

Sparks Specialty Splices

Hidden	No
Hybrid	No
Trailing Flap	No
VT	No
Hybrid VT	No
7/11	No
Urethane Top	No
Urethane Bottom	No
Urethane Splash	No