

Monoflex WS 210

03-644 | Technical Data Sheet



Technical Information

Plies	2
Overall Thickness	.063"
Tensile Force	57# @ 1%
in N/mm	10N/mm
Standard Tension	1%
Min. Pulley	1.5"
Min. Back Flex	1.5"
Weight	.37 Lbs./SF
Product Operational Temp. Range	-22° to 248° F
Hardness	55 Duro Shore A
Max. Width	80"

Material Construction

Conveying Surface

Compound	Silicone/PVC
Cover Surface	.008" Smooth/Glossy
Color	White

Underside

Fabric	Monofilament
Bottom Surface	Fabric
Coefficient of Friction	.2

Standard Fabrications

Longitudinal Splice	Yes
Guide Applied to Cover	No
Sidewalls	No
Edge Capped	No
Cleats	No
Guide Applied to Bottom	Yes
Mechanical Lacing	Yes

Features

FDA	Yes
Anti-Microbial	No
Anti-Static	Yes
Flame Retardant	No
Cross Rigid	Yes
Troughing	No
Curve Belt Compatible	No

Monoflex WS 210

03-644 | Splicing Instructions

High Speed Press Settings

Pressure	24 PSI
Temp. Top	356° F
Temp. Bottom	356° F
Dwell Time	45 Seconds
Foil Position	Inside
Foil	Urethane
Release Top	Gloss
Release Bottom	TFE

Water Cooled Press Settings

Pressure	N/A
Temp. Top	N/A
Temp. Bottom	N/A
Dwell Time	N/A
Foil Position	N/A
Foil	N/A
Release Top	N/A
Release Bottom	N/A



Scan for splicing
demo video

Compatible Splices

Endless Splices

Step Splice	Yes
Straight Finger	No
Split Finger	Yes
Bias Finger	Yes
Skive	No
Finger Over Step	Yes
Step Over Finger	Yes
Electrode	No
Butt Weld	No
Lock Lap	No

Mechanical Splices

Clipper	Yes
Alligator	Yes
Staple	Yes
Minet	No
Plastic Spiral	Yes
Plastic Rivet	Yes
Plastic Hinge	No
Super Screw	No
Bolt Hinge	No
Rivet Hinge	No

Sparks Specialty Splices

Hidden	No
Hybrid	No
Trailing Flap	No
VT	No
Hybrid VT	No
7/11	No
Urethane Top	No
Urethane Bottom	No
Urethane Splash	No
Recessed Lace	No