

*MAB BLU 210

03-059 | Technical Data Sheet



Technical Information

Plies	2
Overall Thickness	.06"
Tensile Force	46# @ 1%
in N/mm	8
Standard Tension	.5%
Min. Pulley	.55"
Min. Back Flex	2"
Weight	.35 Lbs/SF
Product Operational Temp. Range	-4° to 194° F
Hardness	93 Duro Shore A
Max. Width	60"

Material Construction

Conveying Surface

Compound	Polyurethane
Cover Surface	Smooth Matte PU
Color	Blue

Underside

Fabric	Monofilament Polyester
Bottom Surface	PU Impregnated
Coefficient of Friction	.25

Standard Fabrications

Longitudinal Splice	Yes
Guide Applied to Cover	Yes
Sidewalls	Yes
Edge Capped	No
Cleats	Yes
Guide Applied to Bottom	Yes
Mechanical Lacing	Yes

Features

FDA	Yes
Anti-Microbial	Yes
Anti-Static	Yes
Flame Retardant	No
Cross Rigid	Yes
Troughing	No
Curve Belt Compatible	No

*MAB BLU 210

03-059 | Splicing Instructions

High Speed Press Settings

Pressure	24.7 PSI
Temp. Top	342° F
Temp. Bottom	324° F
Dwell Time	30 Seconds
Foil Position	Top
Foil	Blue PU
Release Top	Matte
Release Bottom	TFE

Water Cooled Press Settings

Pressure	30 PSI
Temp. Top	360° F
Temp. Bottom	340° F
Dwell Time	N/A
Foil Position	Top
Foil	Blue PU
Release Top	Matte
Release Bottom	TFE



Scan for splicing demo video

Compatible Splices

Endless Splices

Step Splice	No
Straight Finger	Yes
Split Finger	No
Bias Fiinger	Yes
Skive	No
Finger Over Step	No
Step Over Finger	No
Electrode	No
Butt Weld	No
Lock Lap	No

Mechanical Splices

Clipper	Yes
Alligator	Yes
Staple	Yes
Minet	No
Plastic Spiral	Yes
Plastic Rivet	Yes
Plastic Hinge	No
Super Screw	No
Bolt Hinge	No
Rivet Hinge	No

Sparks Specialty Splices

Hidden	No
Hybrid	No
Trailing Flap	No
VT	No
Hybrid VT	No
7/11	No
Urethane Top	No
Urethane Bottom	No
Urethane Splash	No