


# Monoflex GP 210 MH

03-347 | Technical Data Sheet



## Technical Information

Plies	2
Overall Thickness	.117"
Tensile Force	46# @ 1%
in N/mm	8
Standard Tension	.5%
Min. Pulley	2.4"
Min. Back Flex	3.2"
Weight	.68 Lbs/SF
Product Operational Temp. Range	5° to 176°
Hardness	80 Duro Shore A
Max. Width	118"

## Material Construction

### Conveying Surface

Compound	PVC
Cover Surface	Smooth
Color	Green

### Underside

Fabric	Monofilament Polyester
Bottom Surface	Bare
Coefficient of Friction	.2

## Standard Fabrications

Longitudinal Splice	Yes
Guide Applied to Cover	Yes
Sidewalls	Yes
Edge Capped	No
Cleats	Yes
Guide Applied to Bottom	Yes
Mechanical Lacing	Yes

## Features

FDA	No
Anti-Microbial	No
Anti-Static	Yes
Flame Retardant	No
Cross Rigid	Yes
Troughing	No
Curve Belt Compatible	No

# Monoflex GP 210 MH

03-347 | Splicing Instructions

## High Speed Press Settings

Pressure	29 psi
Temp. Top	355° F
Temp. Bottom	336° F
Dwell Time	90 sec
Foil Position	Inside (SFL)
Foil	Green PVC
Release Top	Smooth
Release Bottom	TFE

## Water Cooled Press Settings

Pressure	25 psi
Temp. Top	360° F
Temp. Bottom	330° F
Dwell Time	4 minutes
Foil Position	Inside (SFL)
Foil	Green PVC
Release Top	Smooth
Release Bottom	TFE



Scan for splicing demo video

## Compatible Splices

### Endless Splices

Step Splice	Yes
Straight Finger	No
Split Finger	Yes
Bias Finger	Yes
Skive	No
Finger Over Step	Yes
Step Over Finger	Yes
Electrode	No
Butt Weld	No
Lock Lap	No

### Mechanical Splices

Clipper	Yes
Alligator	Yes
Staple	Yes
Minet	Yes
Plastic Spiral	Yes
Plastic Rivet	Yes
Plastic Hinge	Yes
Super Screw	No
Bolt Hinge	No
Rivet Hinge	No

### Sparks Specialty Splices

Hidden	No
Hybrid	Yes
Trailing Flap	No
VT	No
Hybrid VT	No
7/11	No
Urethane Top	No
Urethane Bottom	No
Urethane Splash	No