


FRLW 2.0

08-266 | Technical Data Sheet



Technical Information

Plies	1
Overall Thickness	.078"
Tensile Force	28# @ 1%
in N/mm	5
Standard Tension	.50%
Min. Pulley	.375"
Min. Back Flex	1"
Weight	.50 Lbs/sf
Product Operational Temp. Range	-40° to 120° F
Hardness	80 Duro Shore A
Max. Width	60"

Material Construction

Conveying Surface

Compound	Hytrel/Poly
Cover Surface	Smooth
Color	White

Underside

Fabric	Polyester
Bottom Surface	Fabric
Coefficient of Friction	.20

Standard Fabrications

Longitudinal Splice	No
Guide Applied to Cover	Yes
Sidewalls	Yes
Edge Capped	Yes
Cleats	Yes
Guide Applied to Bottom	Yes
Mechanical Lacing	Yes

Features

FDA	Yes
Anti-Microbial	No
Anti-Static	Yes
Flame Retardant	No
Cross Rigid	No
Troughing	Yes
Curve Belt Compatible	No

FRLW 2.0

08-266 | Splicing Instructions

High Speed Press Settings

Pressure	No Settings
Temp. Top	
Temp. Bottom	
Dwell Time	
Foil Position	
Foil	
Release Top	
Release Bottom	

Water Cooled Press Settings

Pressure	No Settings
Temp. Top	
Temp. Bottom	
Dwell Time	
Foil Position	
Foil	
Release Top	
Release Bottom	

Compatible Splices

Endless Splices

Step Splice	No
Straight Finger	Yes
Split Finger	No
Bias Finger	Yes
Skive	No
Finger Over Step	No
Step Over Finger	No
Electrode	Yes
Butt Weld	Yes
Lock Lap	No

Mechanical Splices

Clipper	Yes
Alligator	Yes
Staple	Yes
Minet	No
Plastic Spiral	No
Plastic Rivet	Yes
Plastic Hinge	No
Super Screw	No
Bolt Hinge	No
Rivet Hinge	No

Sparks Specialty Splices

Hidden	No
Hybrid	No
Trailing Flap	No
VT	No
Hybrid VT	No
7/11	No
Urethane Top	No
Urethane Bottom	No
Urethane Splash	No